

EstoWrap 300

High Strength Carbon Fiber Sheet for Structural Strengthening System at Concrete Structure

Description

EstoWrap 300 is a high tensile strength, high elastic modulus sheet of longitudinal oriented continuous carbon fiber element which are held in position by lightweight, open mesh scrim. FRP material can have as much as 10 times the tensile strength of steel. When used in conjunction with a specially developed primer, improves structural performances by strengthening and improving shear strength and deformation properties.

This FRP material design follows the **ACI 440.2R-17** reference standard as the design standard. For composite material pass **ASTM D3039**

Uses

EstoWrap 300 is used for strengthening columns and beams of load bearing structures specifically where improvement to shear strength and deformation properties is required. Typical applications include piers, columns, connecting beams and slabs of railway and road bridges, buildings and tower. In the following structures:

- Commercial, high rise
- Industrial plants
- Warehouse
- Bridges, tunnels, jetties
- Pipes, culvert, chimneys
- Power station plants

Advantages

- Exhibit high tensile strength and elastic modulus
- Good dimensional stability
- High impact resistant
- Resin is of high chemical resistant
- Imparts very low electrical conductivity
- Will not corrode
- Lightweight hence easy to handle and use
- Carbon reinforced hence good thermal expansion
- High shear stress and cut resistance

Durability Description

EstoWrap 300 high performance fabric sheet which is encapsulated in **EstoWrap 300** resin to provide properties of high strength and high elastic modulus. Its low density properties, specific strength and modulus are extremely high compared with conventional materials such as steel and concrete.

EstoWrap 300 is extremely easy to handle and apply with no noise and minimal site equipment necessary allowing quick and easy reinforcement of structural members without major disruption.

EstoWrap 300 is lightweight, has high impact resistant, excellent tensile strength, is extremely stable at high and low temperatures and has excellent chemical resistance under a variety of exposure conditions.

Physical Properties

Product Name	Areal Weight (g/m ²)	Fabric Thickness (mm)
EstoWrap 300	300	0.167

Dry Properties

Type	High strength Carbon Fiber
Fiber Tensile Strength	4900 N/mm ²
Density	1.8 – 2.0 g/cm ³
Elongation at break	2.1 %
Fiber Tensile E-modulus	240 GPa
Style	Woven UD
Rupture Strength	Min 2.5 %

Composite Gross Properties

Laminate thickness	>0.8 mm
Elongation/strain (ASTM D3039)	2.1 %
Bond strength (ASTM D7522)	>1.4Mpa Concrete failure (refer ACI 440.2R-17)
Tensile modulus (ASTM D3039) design value	>230 Gpa

Instruction to Use

Preparation

Concrete surface must be dry, smooth, sound free from debris and loose material. Surfaces must be fully cured and free from contamination.

Thorough preparation of the substrate is vital with light grit blasting recommended to remove all deleterious substances and provide a suitable key. All dust and debris must be removed prior to proceeding.

Priming

The base and hardener components of EstoWrap Primer should be thoroughly stirred before the two are mixed together.

Pour hardener into suitably sized mixing vessel and add the base resin into the hardener. The use of heavy duty slow speed, flameproof or air driven drill fitted with a mixing paddle is desirable. Mix these components in the quantities supplied taking care to ensure all containers are scraped clean.

Apply EstoWrap Primer to the prepared substrate using a stiff brush, working the primer well into the substrate at a coverage rate of 0.3 kg/m²

Application

Arrange enough material, manpower and equipment to carry out the application within the resin pot life. The base and hardener components of EstoWrap Resin should be mixed as per mixing instruction of EstoWrap Primer. Apply the EstoWrap Resin to primed surface, using roller at the rate of 0.6 kg/m². Immediately after application of the resin, the pre-cut EstoWrap 300 Carbon Fabric Sheet (maximum 4m length) should be applied using rubber or plastic scraper. Remove the release paper from the EstoWrap 300 Carbon Fabric sheet and roll it with an impregnation roller in a direction parallel to the fibers in the carbon sheet. After 30 minutes of the impregnation and within 3 hours, apply a second coat of EstoWrap Resin at a coverage rate of 0.6 kg/m² to completely encapsulate EstoWrap 300 Carbon Fabric Sheet.

Rev V/tech/24L02

Other Applications

EstoWrap 300 can be used as external strengthening nearly anywhere additional reinforcement is required.
 Blast mitigation for concrete and masonry walls
 Strengthening for pressure in pipes, silos, and tanks
 Reinforce around steel, slab and wall openings
 Strengthening domes, tunnels, and chimneys

Limitation

EstoWrap 300 should be protected via over coating with a PU based UV resistant coating within 6 hours of application.

Packaging

EstoWrap 300 Carbon Fiber Sheet
 0.5m(W) x 100m (L)

Packaging

EstoWrap Resin

Hardener	5 kg
Base	10 kg

Coverage

EstoWrap Primer	0.3kg/m ²
EstoWrap Resin	1.2 kg/m ² /2 coats

Technical Support

Estop offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance.

Storage

Store on pallets in dry conditions. EstoWrap Primer has a shelf life of 12 months, If stored in extreme heat condition, the shelf life may be reduced.

However, **EstoWrap 300** Carbon Fiber Sheet have an unlimited shelf life but must be stored in dry condition.

Additional Information

Estop manufactures and offers a wide range of complementary products, which includes waterstops, waterproofing products, grouts, anchors, specialized flooring products. In addition, a wide range of products formulated for repair and refurbishment of spalled concrete are available.

Important Note

Estop products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which may be obtained on request. Whilst Estop endeavors to ensure that any advice, recommendation, specification or information in may give is accurate and correct, it shall not, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it.